


contract selection
cat. A

bolzan

GRISÙ



COMPOSITION

68% polyester - 32% polypropylene

COLOUR FASTNESS TO LIGHT

> 6, ISO 105-B02

PILLING

4/5, ISO 12945-2

MARTINDALE

>135.000 rubs ISO 12947-2

FASTNESS TO RUBBING

dry 4/5, wet 4, ISO 105 X12

SEAM SLIPPAGE

warp 3 mm, weft 3 mm, ISO 13936-2



FIRETEST

11M-UNI 9175; classe 1 - UNI 9177; EN 1021 1/2; BS 5852 part 1; DIN 4102 B1; NF D 60 013; California TB 117-2013; IMO FTP Code 307 part 8; ÖNORM B 3825; cigarette BS5852 crib 5 upon request

SOUND ABSORPTION

Δw 0,75 arricciato; Δw 0,60 teso;
ISO 354 - allestimento G.

CARE











I colori e i materiali riprodotti nelle immagini hanno un valore puramente indicativo. Eventuali differenze cromatiche con i colori reali non costituiscono motivo di contestazione.

Colors and materials in the images are purely indicative. Any chromatic differences with the real colors do not constitute grounds for dispute.




I colori e i materiali riprodotti nelle immagini hanno un valore puramente indicativo. Eventuali differenze cromatiche con i colori reali non costituiscono motivo di contestazione.

Colors and materials in the images are purely indicative. Any chromatic differences with the real colors do not constitute grounds for dispute.



TOUCH ME



COMPOSITION

80% PL 20%resin (water repellent)

COLOUR FASTNESS TO LIGHT

4, ISO 105 B02

PILLING

4, ISO 12945-2

MARTINDALE

30.000 rubs ISO 12947-2


FASTNESS TO RUBBIING

dry 4/5, wet 4, ISO 105 X12

FIRETEST

11M - UNI 9175;
EN 1021 part 1/2;
BS 5852 part 1, is 0 and 1;
BS 5852 crib 5;
DIN 4102 B1;
California TB 117-2013.

CARE



I colori e i materiali riprodotti nelle immagini hanno un valore puramente indicativo. Eventuali differenze cromatiche con i colori reali non costituiscono motivo di contestazione.

Colors and materials in the images are purely indicative. Any chromatic differences with the real colors do not constitute grounds for dispute.

NO FIRE WOOL



COMPOSITION

100% PL FR

COLOUR FASTNESS TO LIGHT

4, xenotest

PILLING

3, ISO 12945-2

MARTINDALE

70.000 rubs BSI 6590




FIRETEST

CLASS 1 (Italy), M1 (France), B1 (Germany),
CLASS 1 (Europe), IMO MED

NOTE

certificato Oeko tex

CARE




I colori e i materiali riprodotti nelle immagini hanno un valore puramente indicativo. Eventuali differenze cromatiche con i colori reali non costituiscono motivo di contestazione.

Colors and materials in the images are purely indicative. Any chromatic differences with the real colors do not constitute grounds for dispute.

cat. **A**

bolzan

MARLUCH



COMPOSITION

38% acrylic
28% polyester
20% cotton
14% wool

**COLOUR FASTNESS
TO LIGHT**

Note 5-6
UNI EN ISO 105-B02

PILLING

Note 5
UNI EN ISO 12945-2


MARTINDALE

100.000 rubs
UNI EN ISO 12947-2

FIRETEST



EN 1021 part 1-2
UNI 9175 classe 11M
BS5852 source 0 and 1

CARE




NOTES

Slight differences in colour may occur



02




05




06




07



09



11



01



12

GUBBIO | TORRILANA



COMPOSITION

48% CO- 15% VI- 7%LI- 30%PL

COLOUR FASTNESS

TO LIGHT

Light colour 4-5 / Medium-Dark colour 5
UNI EN ISO 105-B02

PILLING

grade 4 (change at 5000 turns)
UNI EN ISO 12945-2:2002

MARTINDALE

52000 cycles+/-10%
UNI EN ISO 12947-2:2000

FIRETEST








BS 5852-1 (1979) CIGARETTE
BS 5852:2006 CIGARETTE
BS 5852-1 1979)MATCH interliner
BS 5852:2006 MATCH
CAL TB 117:2013
1021-1:1:2014 CIGARETTE
1021-1:1:2014 MATCH

CARE



NOTES

Slight differences in colour may occur



PARADISE | TORRILANA



COMPOSITION

13% CO- 30% WO- 25% PC- 30% PL- 2% PA

COLOUR FASTNESS

TO LIGHT

Light colour 4-5 / Medium-Dark colour 5
UNI EN ISO 105-B02

PILLING

grade 4 (change at 5000 turns)
UNI EN ISO 12945-2:2002


MARTINDALE

35000 cycles+/-10%
UNI EN ISO 12947-2:2000

FIRETEST


BS 5852-1 (1979) CIGARETTE
BS 5852-1 (1979) MATCH
CAL TB 117:2013

CARE




NOTES

Slight differences in colour may occur



VIRGOLO | TORRILANA



COMPOSITION

75% CO - 18% PL - 7% PA

COLOUR FASTNESS

TO LIGHT

Light colour 4-5 / Medium-Dark colour 5
UNI EN ISO 105-B02

PILLING

grade 3/4 (change at 5000 turns)
UNI EN ISO 12945-2:2002


MARTINDALE

70.000 cycles+/-10%
UNI EN ISO 12947-2:2000

FIRETEST








BS 5852-1 (1979) CIGARETTE
BS 5852-1 (1979) MATCH
BS 5852:2006 CIGARETTE
CAL TB 117:2013

CARE



NOTES

Slight differences in colour may occur



bolzan